

C10: HiCap™ premium multi mode 62.5 μm fibre

Properties of cabled OM1 fibre optimised for 1 Gigabit Ethernet applications

General and application

This HiCap™ fibre is optimised for Gigabit Ethernet transmission (1000Base-FX). It is suitable for transmission speeds of up to 10 Gb/s. In addition it gives an improved range at 850 nm and a further improved range at 1300 nm. HiCap multimode fibres eliminate the need to use a mode conditioning patch cords for LX (1300 nm) systems.

Standards and Norms

IEC 60793-2-10 Category A1b	ISO/IEC 11801:2002 category OM1
EN 60793-2-10: type A1b	IEEE 802.3 - 2002. with amendment 802.3ae - 2002.
TIA/EIA-492 AAAB	ANSI/TIA/EIA-568.B.3 – 2000
EN 50173-1:2007 category OM1	IEC 9314-3

Cable attenuation

IEC 60793-1-40

850 nm	≤ 3.2 dB/km
1300 nm	≤ 1.0 dB/km
Inhomogeneity of OTDR trace for any two 1000 metre fibre lengths	Max. 0.2 dB/km

Bandwidth

IEC 60793-1-41

850 nm	200 MHz • km
1300 nm	600 MHz • km

Group index of refraction

IEC 60793-1-22

Group index of refraction at 850 nm	1.496
Group index of refraction at 1300 nm	1.481

Other properties

IEC 60793-1-xx

Attribute	Measurement method	Units	Limits
Core diameter	IEC/EN 60793-1-20	μm	62.5 ± 2.5
Cladding diameter	IEC/EN 60793-1-20	μm	125.0 ± 1.0
Cladding non-circularity	IEC/EN 60793-1-20	%	≤ 1.0
Core non-circularity	IEC/EN 60793-1-20	%	≤ 5
Core-cladding concentricity error	IEC/EN 60793-1-20	μm	≤ 1.5
Primary coating diameter - uncoloured	IEC/EN 60793-1-21	μm	242 ± 7
Primary coating diameter - coloured	IEC/EN 60793-1-21	μm	250 ± 15
Primary coating non-circularity	IEC/EN 60793-1-21	%	≤ 5
Primary coating-cladding concentricity error	IEC/EN 60793-1-21	μm	≤ 10
Proof stress level	IEC/EN 60793-1-30	GPa	≥ 0.7 (≈ 1 %)
Typical average strip force	IEC/EN 60793-1-32	N	1.7
Strip force (peak)	IEC/EN 60793-1-32	N	1.3 ≤ F _{peak,strip} ≤ 8.9
Numerical aperture	IEC/EN 60793-1-43		0.200 ± 0.015